



# POLYTURF PLUS PAD & POUR





.....  
**COLOR OPTIONS**



# COLOR OPTIONS

DESERT 1200-0015	SMOOTHIE 1200-0068	CLASSIC TAN 1200-0089	BEIGE 1200-0133	GALLANT GOLD 1200-0123	OCEAN BLUE 1200-0011	ROYAL BLUE 1200-0037	BLUE CHIP 1200-0063	TARKETT BLUE 1200-0092	POOL BLUE 1200-0096
GOLD 1200-0043	PURDUE GOLD 1200-0162	GREY 1200-0060	DOLPHIN GREY 1200-0004	MORNING FOG 1200-0066	BLUE JAY 1200-0125	SOUTHERN BLUE 1200-0168	BLUE BLOOD 1200-0184	MIDNIGHT BLUE 1200-0181	DEEP BLUE 1200-0111
GREY SMOKE 1200-0077	LIGHT GREY 1200-0083	GREY CLOUD 1200-0085	STORM GREY 1200-0102	GAUNTLET GREY 1200-0154	DARK NAVY BLUE 1200-0081	CHAPEL HILL BLUE 1200-0073	BRIGHT RED 1200-0044	REAL RED 1200-0084	SUNDRIED TOMATO 1200-0122
MID-GREY 1200-0180	GREY SCREEN 1200-0184	GREEN 1200-0113	GARDEN GREEN 1200-0062	SAGE GREEN 1200-0006	RED THEATRE 1200-0182	ORANGE 1200-0094	BRIGHT ORANGE 1200-0065	YELLOW 1200-0095	VIBRANT YELLOW 1200-0149
GRASS GREEN 1200-0093	TROPICAL GREEN 1200-0135	GARDEN CUCUMBER 1200-0155	BOYDEN GREEN 1200-0169	BLUE 1200-0161	BUTTERFIELD YELLOW 1200-0177	PINK PANTHER 1200-0186	PURPLE 1200-0175	BLACK 1200-0091	WHITE 1200-0090

# TECHNICAL DATA

CERTIFICATION & CLASSIFICATION	STANDARDS	POLYTURF PLUS PAD & POUR 4+2	POLYTURF PLUS PAD & POUR 7+2	POLYTURF PLUS PAD & POUR 9+2	POLYTURF PLUS PAD & POUR 12+2
<b>TECHNICAL CHARACTERISTICS</b>					
Total Thickness		6.0 mm (0.236")	9.0 mm (0.354")	11.0 mm (0.433")	14.0 mm (0.551")
Weight (Base Mat)		2.59 kg/m2 (0.53 lbs./sq. ft.)	4.5 kg/m2 (0.93 lbs./sq. ft.)	5.86 kg/m2 (1.2 lbs./sq. ft.)	7.82 kg/m2 (1.6 lbs./sq. ft.)
Roll Width (Base Mat)		1.5 m (59")	1.5 m (59")	1.5 m (59")	1.5 m (59")
Roll Length (Base Mat)		25 m (82')	25 m (82')	25 m (82')	25 m (82')
<b>SPORTS CHARACTERISTICS</b>					
Surface Finish Effect	ASTM F2772-11	Passed	Passed	Passed	Passed
Force Reduction	ASTM F2772-11	Class 1	Class 2	Class 2	Class 3
Vertical Deformation	ASTM F2772-11	Passed	Passed	Passed	Passed
Ball Rebound	ASTM F2772-11	Passed	Passed	Passed	Passed
<b>TECHNICAL REQUIREMENTS</b>					
Reaction to Fire	ASTM E648	Class 1 (Radiant Panel)	Class 1 (Radiant Panel)	Class 1 (Radiant Panel)	Class 1 (Radiant Panel)
Shore Hardness		80 (Shore A)	80 (Shore A)	80 (Shore A)	80 (Shore A)
Tensile Strength	ASTM D412	3200 PSI	3200 PSI	3200 PSI	3200 PSI
Elongation	ASTM D412	340%	340%	340%	340%
Tear Strength	ASTM D624	360 PLI	360 PLI	360 PLI	360 PLI
Health Certifications					
<b>COLORS</b>					
		50 Colors	50 Colors	50 Colors	50 Colors
<b>WARRANTY</b>					
Product and Wear		30 years	30 years	30years	30 years
Moisture Tolerance		10 years	10 years	10 years	10 years